

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 04221047
PUBLICATION DATE : 11-08-92

APPLICATION DATE : 19-12-90
APPLICATION NUMBER : 02418065

APPLICANT : KUBOTA CORP;

INVENTOR : KATAYAMA YOSHIO;

INT.CL. : C22C 38/00 C22C 38/30

TITLE : HIGH SPEED STEEL TYPE SINTERED ALLOY

ABSTRACT : PURPOSE: To improve strength, wear resistance, surface roughing resistance, pitting corrosion resistance, and seizure resistance by specifying respective contents of C, Si, Mn, Cr, Mo, W, Co, etc., in a sintered alloy.

CONSTITUTION: The sintered alloy has a composition consisting of, by weight $\leq 1.7\%$ C, $>0.6-3.5\%$ Si, $\leq 0.6\%$ Mn, $3-8\%$ Cr, $3-9\%$ Mo, $5-14\%$ W, $7-14\%$ Co, $\leq 8\%$ of one or ≥ 2 elements among V, Ti, and Nb, and the balance essentially Fe. Further, if necessary, either or both of $\leq 2\%$ B and $\leq 3\%$ Ni are substituted for a part of Fe. If HIP sintering, etc., are applied to this alloy, the high-density high speed steel type sintered alloy can be formed. By using this sintered alloy as a rolling roll barrel member, roll life can be prolonged.

COPYRIGHT: (C)1992,JPO&Japio